

TEST REPORT

DATE: 07-08-2020	-08-2020 Page 1 of 1	
CLIENT	Fabric Sources International	
TEST METHOD CONDUCTED	ASTM F3352 Standard Specification for Isolation Gowns Intend for Use in Healthcare Facilities	

	DESCRIPTION OF TEST SAMPLE		
IDENTIFICATION	FSI-P-45		

GENERAL PRINCIPLE

This specification provides requirements for isolation gowns used for protection of healthcare workers where the potential for exposure to blood, body fluids, and other potentially infectious materials exists. The specification requires barrier testing based on the system of classifying gowns established in AAMI PB70 and sets general safety requirements for gowns. Documentation and reporting requirements are set for important physical properties including tensile strength, tear resistance, seam strength, and barrier performance.

TEST RESULTS

TEST METHOD	CRITERION	RESULTS	QUALIFICATION Per Table 1 and 2
ASTM D5034 Breaking/Tensile Strength	≥30 N (7.0 lbf)	Machine - 17.4 lbf Cross - 12.9 lbf	Meets level 1, 2 and 3
ASTM D5587/D5733 Tear Strength	≥10 N (2.3 lbf)	Machine – 7.6 lbf Cross – 26.9 lbf	Meets level 1, 2 and 3
ASTM D1683 Seam Strength	≥30 N (7.0 lbf)	N/A	N/A
AATCC 42 Water Impact Penetration	#1- <4.5 g AQL 4.0 #2- <1.0 g AQL 4.0 #3- <1.0 g AQL 4.0	0 g	Meets level 1 and 2
AATCC 127 Hydrostatic Resistance	#1- None #2- >20cm AQL 4.0 #3- >50cm AQL 4.0	270 cm	Meets level 1 and 2

This finished material meest ANSI/AAMI PB70 Level 2 Isolation Gown fabric.

APPROVED BY: Lary aflury

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.